

Schulink XL 350-S

Crosslinked Polyethylene
LyondellBasell Industries
Rotomolding

General			
Features	• UV Stabilized		
Uses	• Agricultural Applications • Automotive Under the Hood • High Temperature Applications • Lawn and Garden Equipment • Tanks		
Appearance	• Black • Natural Color		
Forms	• Pellets • Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	0.944	0.942 g/cm ³	ASTM D792
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
100% Igepal, Compression Molded, F50	> 1000 hr	> 1000 hr	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield, Rotational Molded)	2800 psi	19.3 MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Break, Rotational Molded	350 %	350 %	
Flexural Modulus - 1% Secant (Rotational Molded)	102000 psi	703 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 In (3.18 Mm), Rotational Molded	61 ft·lb	83 J	
-40°F (-40°C), 0.250 In (6.35 Mm), Rotational Molded	> 185 ft·lb	> 251 J	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed, Rotational Molded	145 °F	63.0 °C	
264 Psi (1.8 Mpa), Unannealed, Rotational Molded	97.5 °F	36.4 °C	

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (Any Color)	HB	HB	UL 94

Notes

¹ Compression Molded

² 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.

