

Technical Data Sheet
Alcryn® 2060 CL
Melt Processable Rubber
Engineering Plastics



General			
Additive	• UV Stabilizer		
Features	• High Flow • High Heat Resistance • Noise Damping • Oil Resistant • Ozone Resistant • UV Resistant • Vibration Damping • Weather Resistant		
Uses	• Cable Jacketing • Engineering Parts • Fabrics • Gaskets • Handles • Hose • Seals • Sheet • Tubing • Weatherstripping • Wire Jacketing		
Agency Ratings	• EU 2002/96/EC (WEEE)		
RoHS Compliance	• RoHS Compliant		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Blow Molding • Compression Molding • Extrusion • Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.12	1.12 g/cm³	ASTM D792
--	1.12 g/cm³	1.12 g/cm³	ISO 1183
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
0.0750 in (1.91 mm), Compression Molded	435 psi	3.00 MPa	ASTM D638 ISO 527-2
Tensile Strength			
Yield, 0.0750 in (1.91 mm), Compression Molded	1050 psi	7.24 MPa	ASTM D638 ISO 527-2
Tensile Elongation			
Break, 0.0750 in (1.91 mm), Compression Molded	380 %	380 %	ASTM D638 ISO 527-2
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Set	12 %	12 %	ASTM D412
Tear Strength ¹ (75°F (24°C))	150 lbf/in	26.3 kN/m	ASTM D624
Compression Set			
75°F (24°C), 22 hr	27 %	27 %	ASTM D395B ISO 815
212°F (100°C), 22 hr	69 %	69 %	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			
Shore A, 0.0750 in (1.91 mm), Compression Molded	60	60	ASTM D2240
IRHD Hardness	60	60	ISO 48



Technical Data Sheet
Alcryn® 2060 CL
Melt Processable Rubber
Engineering Plastics



Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Change in Shore Hardness in Air 257°F (125°C), 168 hr	61	61	ISO 188
Change in Ultimate Elongation 257°F (125°C), 168 hr	380 %	380 %	ASTM D471
Change in Durometer Hardness 257°F (125°C), 168 hr	61	61	ASTM D471
Change in Volume 75°F (24°C), 168 hr, in Reference Fuel B	8.0 %	8.0 %	ASTM D471
212°F (100°C), 168 hr, in ASTM #1 Oil	-30 %	-30 %	
212°F (100°C), 168 hr, in ASTM #3 Oil	-6.0 %	-6.0 %	
212°F (100°C), 168 hr, in Water	9.0 %	9.0 %	

Additional Information

The value listed as Density-Specific Gravity, ASTM D792, was tested in accordance with ASTM D471.

Aging Tensile Strength, ASTM D573, 7 days, 257°F: 1128psi

Aging 100% Modulus, ASTM D573, 7 days, 257 °F: 509psi

Aging Elongation At Break, ASTM D573 and ISO 188: 375%

Fluid Resistance 7 Days in water, ISO 1817, at 212 °F: 9%

Fluid Resistance 7 Days in ASTM Oil no. 1, ISO 1817, at 212 °F: -30%


Fluid Resistance 7 Days in IRM 903 Oil no. 3, ISO 1817, at 212 °F: -6%

Fluid Resistance 7 Days in ASTM Ref. Fuel no. B, ISO 1817, at 75 °F: 8%

Rheological Viscosity, ASTM D3835, 1/300s at 374°F: 247Pa-s



Technical Data Sheet
Alcryn® 2060 CL
Melt Processable Rubber
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	350 °F	177 °C

Notes
¹ Die C

Notes
These are typical property values not to be construed as specification limits.

