

Alcryn 2060 NC

Melt Processable Rubber

LyondellBasell Industries

Engineering Plastics

General			
Features	- Fast Molding Cycle - General Purpose - High Flow	- High Heat Resistance - Noise Damping - Oil Resistant	- Ozone Resistant - Recyclable Material - Vibration Damping
Uses	- Cable Jacketing - Coating Applications - Fabric Coatings - Flexible Grips - Gaskets	- General Purpose - Handles - Hose - Overmolding - Profiles	- Seals - Tubing - Weatherstripping - Wire & Cable Applications
RoHS Compliance	• RoHS Compliant		
UL File Number/Usa	• E51193		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	- Blow Molding - Extrusion	- Injection Molding - Vacuum Forming	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.12	1.12 g/cm ³	ASTM D471
--	1.12 g/cm ³	1.12 g/cm ³	ISO 2781

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Taber Abrasion Resistance			ASTM D1044
1000 Cycles, 1000 G, Cs-17 Wheel	5.00 mg	5.00 mg	
Torsion Modulus ¹			ASTM D1043
-4°F (-20°C), 74.8 Mil (1.90 Mm)	696 psi	4.80 MPa	
75°F (24°C), 74.8 Mil (1.90 Mm)	334 psi	2.30 MPa	

Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Set ²	8 %	8 %	ASTM D412
Tensile Stress			
100% Strain, 0.0748 In (1.90 Mm) ¹	435 psi	3.00 MPa	ASTM D412 ISO 37
100% Strain, 257°F (125°C), 0.0748 In (1.90 Mm) ³	392 psi	2.70 MPa	ASTM D573 ISO 188
Tensile Strength			
Yield, 0.0748 In (1.90 Mm) ¹	1150 psi	7.90 MPa	ASTM D412 ISO 37
Yield, 257°F (125°C), 0.0748 In (1.90 Mm) ³	943 psi	6.50 MPa	ASTM D573 ISO 188
Tensile Elongation			
Break, 0.0748 In (1.90 Mm) ¹	420 %	420 %	ASTM D412 ISO 37
Break, 257°F (125°C), 0.0748 In (1.90 Mm) ³	340 %	340 %	ASTM D573 ISO 188
Tear Strength ^{4, 1} (0.0748 In (1.90 Mm))	160 lbf/in	28.0 kN/m	ASTM D624
Compression Set ⁵			ASTM D395B ISO 815
75°F (24°C), 22 Hr	13 %	13 %	
212°F (100°C), 22 Hr	62 %	62 %	
Clash-Berg Modulus (-44°F (-42°C))	10000 psi	68.9 MPa	ASTM D1043



Alcryn 2060 NC

Melt Processable Rubber

LyondellBasell Industries


Engineering Plastics

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A, 0.0748 In (1.90 Mm), Compression Molded	59	59	ISO 868
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-121 °F	-85.0 °C	ASTM D746
			ISO 812
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Change in Durometer Hardness in Air ²			ASTM D573
Shore A, 257°F (125°C), 168 Hr	1.0	1.0	ISO 188
Change in Volume ²			ASTM D471
81°F (27°C), 168 Hr, In Reference Fuel B	17 %	17 %	ISO 1817
212°F (100°C), 168 Hr, In Astm #1 Oil	-21 %	-21 %	
212°F (100°C), 168 Hr, In Irm 903 Oil	17 %	17 %	
212°F (100°C), 168 Hr, In Water	8.0 %	8.0 %	
Fill Analysis	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Viscosity (374°F (190°C), 300 Sec ⁻¹)	350 Pa·s	350 Pa·s	ASTM D3835



Alcryn 2060 NC

Melt Processable Rubber
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	351 °F	177 °C

Notes

- ¹ Compression Molded
- ² 1.9 mm, Compression Molded
- ³ 7 days, Compression Molded
- ⁴ Die C
- ⁵ Type I pellets, 12.7 mm diameter, plied up from 1.9 mm slabs

Notes

These are typical property values not to be construed as specification limits.

