

Technical Data Sheet
Alcryn® 2160 NC
Melt Processable Rubber
Engineering Plastics



General			
Features	• Abrasion Resistant • Chemical Resistant	• Good Tear Strength • High Flow	• High Friction
Uses	• Automotive Interior Parts • Cable Jacketing • Gaskets	• Handles • Hose • Seals	• Tubing • Weatherstripping • Wire Jacketing
Agency Ratings	• EU 2002/96/EC (WEEE)		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	1.15	1.15 g/cm³	ASTM D792
--	1.15 g/cm³	1.15 g/cm³	ISO 1183

Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress			
100% Strain	348 psi	2.40 MPa	ASTM D412
100% Strain, 0.0748 in (1.90 mm)	348 psi	2.40 MPa	ISO 37
Tensile Strength			ASTM D412
Break, 0.0748 in (1.90 mm)	1780 psi	12.3 MPa	ISO 37
Tensile Elongation			
Break	630 %	630 %	ASTM D412
Break, 0.0748 in (1.90 mm)	630 %	630 %	ISO 37
Tear Strength ¹ (75°F (24°C))	297 lbf/in	52.0 kN/m	ASTM D624
Compression Set			ASTM D395
75°F (24°C), 22 hr	18 %	18 %	ISO 815
212°F (100°C), 22 hr	86 %	86 %	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A, 0.0748 in (1.90 mm), Compression Molded	59	59	ISO 868

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-86.8 °F	-66.0 °C	ASTM D746 ISO 812



Technical Data Sheet
Alcryn® 2160 NC
Melt Processable Rubber
Engineering Plastics



Additional Information

The value listed as Specific Gravity, ASTM D792, was tested in accordance with ASTM D471.
The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.
The value listed as Shore Hardness, ISO 868, was tested in accordance with ISO 48.
Permanent Set (Tension), ASTM D412, Compression Molding, 1.9 mm: 14%
100% Modulus, ASTM D412, ISO 37, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 132%
Tensile Strength, ASTM D412, ISO 37, DIN 53504, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 99%
Elongation At Break, ASTM D412, ISO 37, Physical Retention After 7 Days at 125°C, Compression Molding, 1.9 mm: 114%
Hardness, ISO 48, Physical Retention After 7 Days at 125°C, Shore A, Compression Molding, 1.9 mm: 54
Viscosity, ASTM D3835, 300 s-1 at 190°C, Compression Molding, 1.9 mm: 255 Pa*s
Typical Processing Temperature, Compression Molding, 1.9 mm: 177° C
Volume Change, ASTM D471, ISO 1817, After 7 days, 100°C, Water, Compression Molding, 1.9 mm: 13%
Volume Change, After 7 days, ASTM D471, ISO 1817, 24°C, Fuel B, Compression Molding, 1.9 mm: 11%
Volume Change, After 7 days, ASTM D471, ISO 1817, 100°C, ASTM #1 Oil, Compression Molding, 1.9 mm: -23%
Volume Change, After 7 days, ASTM D471, ISO 1817, 100°C, IRM 903 Oil #3, Compression Molding, 1.9 mm: 1%
Clash-Berg Stiffness Temperature, ASTM D1043, 10000 psi, Compression Molding, 1.9 mm: -43° C

Notes

¹ Die C

Notes

These are typical property values not to be construed as specification limits.

