

Technical Data Sheet

Hostalen ACP 5331H

High Density Polyethylene



Product Description

Hostalen ACP 5331 H is a state of the art HDPE resin, produced by latest Hostalen ACP technology.

Hostalen ACP 5331 H is easy processable on injection moulding and compression moulding equipment.

Exceptional organoleptic properties and a good balance of stiffness, toughness and environmental stress cracking resistance make Hostalen ACP 5331 H the choice of customers for the production of closures for sparkling water, CSD and many other types of food and nonfood caps and closures as well as tube shoulders.

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Caps & Closures; Collapsible Tubes
Market	Consumer Products; Rigid Packaging
Processing Method	Compression Molding; Injection Molding
Attribute	Good ESCR (Environmental Stress Cracking Resistance); Good Organoleptic Properties; Good Toughness; High Density

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate			
(190 °C/2.16 kg)	2.1	g/10 min	ISO 1133-1
(190 °C/5.0 kg)	6.3	g/10 min	ISO 1133-1
Density	0.953	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1150	MPa	ISO 527-1, -2
Tensile Stress at Yield	30	MPa	ISO 527-1, -2
Tensile Strain at Yield	10	%	ISO 527-1, -2
FNCT, (6.0 MPa, 2% Arkopal N100, 50 °C)	>9	hr	ISO 16770
Impact			
Charpy Impact Strength - Notched			
(23 °C)	7	kJ/m ²	ISO 179
(-30 °C)	5	kJ/m ²	ISO 179
Hardness			
Shore Hardness, (Shore D)	62		ISO 868
Ball Indentation Hardness	51	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B50)	75	°C	ISO 306

