

Technical Data Sheet

Lufflexen hyPE 52R FA

High Density Polyethylene



Product Description

Lufflexen hyPE 52R FA is a high performance, high density polyethylene grade. This grade contains hexene as comonomer and offers good processability in a broad processing window. Lufflexen hyPE 52R FA can be used in blown and cast films, textile and stretched applications. It contains antioxidants and is delivered in pellet form.

This product is not intended for use in medical and pharmaceutical applications.

Status	Commercial: Active
Availability	Europe
Application	Food Packaging Film; Lamination Film; Nets
Market	Flexible Packaging; Textile
Processing Method	Blown Film; Cast Film; Monofilament
Attribute	Antioxidant; Good Flow; High Stiffness; Low Gel

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	2.0	g/10 min	ISO 1133-1
Density	0.952	g/cm ³	ISO 1183-1
Film			
Tensile Strength			
MD	48	MPa	ISO 527-1, -3
TD	46	MPa	ISO 527-1, -3
Tensile Elongation at Break			
MD	1000	%	ISO 527-1, -3
TD	1000	%	ISO 527-1, -3
Elmendorf Tear Strength			
MD	65	g	ASTM D1922
TD	190	g	ASTM D1922
Thermal			
Peak Melting Point	131	°C	ISO 11357-3
Optical			
Haze	< 30	%	ASTM D1003
Gloss, (45°)	> 45		ASTM D2457
Additional Information			
Test Specimen	Film		

Film properties tested using 50 µm thickness blown film extruded at a melt temperature of 225°C and a blow-up ratio of 2.5:1.



Processing Parameters

Extrusion Temperature

170-240 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

In cases where higher temperatures are required, please contact your appropriate technical contact for support.

Further Information

Health and Safety:

The resin is manufactured to the highest standards, but special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off-line operations. The products of degradation may have an unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention should be observed.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

Recycled resins may have previously been used as packaging for, or may have otherwise been in contact with, hazardous goods. Converters are responsible for taking all necessary precautions to ensure that recycled resins are safe for continued use.

For further information about safety in handling and processing please refer to the Safety Data Sheet.

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks.

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

