

Technical Data Sheet

Petrothene LB832002

High Density Polyethylene



Product Description

Petrothene LB832002 is a high density polyethylene resin selected by customers for sheet extrusion and thermoforming. LB832002 exhibits very low sag, high stiffness and good chemical resistance.

Application	General Sheet Extrusion
Market	Rigid Packaging
Processing Method	Sheet and Profile Extrusion
Attribute	High Stiffness

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.29	g/10 min	0.29	g/10 min	ASTM D1238
Density, (23 °C)	0.962	g/cm ³	0.962	g/cm ³	ASTM D1505
Mechanical					
Flexural Modulus					
(1% Secant)	250000	psi	1720	MPa	ASTM D790
(2% Secant)	205000	psi	1410	MPa	ASTM D790
Tensile Strength at Yield	4600	psi	31.7	MPa	ASTM D638
Tensile Elongation at Break	>600	%	>600	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	67		67		ASTM D2240
Thermal					
Vicat Softening Temperature	268	°F	131	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746

