

High Flow ABS POLYLAC® PA-716

Product Description: High flow, Medium impact

Properties	ISO Test Method	Test Condition	Unit	PA-716
Melt Flow Index	1133	220°C×10KG	ml/10 min	33
Mass Density	1183	23 °C	g/cm ³	1.04
Tensile Strength	527	50 mm/min, yield	MPa	42
		50 mm/min, break	MPa	31
Tensile Elongation	527	50 mm/min	%	25
Flexural Strength	178	2 mm/min	MPa	65
Flexural Modulus		2 mm/min	GPa	1.9
Izod Impact Strength	180/1A	23 °C Notched	KJ/m ²	25
		-30 °C Notched	KJ/m ²	11
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	26
		-30 °C Notched	KJ/m ²	12
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	104
		5 Kg,50 °C/hr	°C	96
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	83
		1.8 MPa Annealed	°C	97
Coefficient of Linear Thermal Expansion	11359	-	-	9.1 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.4~0.7
Symbol	1043	-	-	>ABS<

