

High Flow ABS POLYLAC® PA-746H

Product Description: Super high flow,High impact

Properties	ISO Test Method	Test Condition	Unit	PA-746H
Melt Flow Index	1133	220°C×10KG	ml/10 min	40
Mass Density	1183	23 °C	g/cm ³	1.03
Tensile Strength	527	50 mm/min, yield	MPa	37
		50 mm/min, break	MPa	27
Tensile Elongation	527	50 mm/min	%	60
Flexural Strength	178	2 mm/min	MPa	54
Flexural Modulus		2 mm/min	GPa	1.7
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	27
		-30°C, Notched	KJ/m ²	12
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	28
		-30 °C Notched	KJ/m ²	14
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	102
		5 Kg,50 °C/hr	°C	94
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	81
		1.8 MPa Annealed	°C	96
Coefficient of Linear Thermal Expansion	11359	-	-	9.2 x 10-5
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.4~0.7
Symbol	1043	-	-	>ABS<

