

Flame Retardant ABS POLYLAC® Characteristics PA-764

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	防火級 FLAME RETARDANT
				PA-764
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	3.2
比重 Mass Density	D792	23 °C	-	1.19
硬度 Hardness	D785	-	R Scale	98
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	370
			lb/in ²	5250
延伸率 Tensile Elongation	D638	6 mm/min	%	15
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	590
			lb/in ²	8360
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.0
			10 ⁵ lb/in ²	2.8
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	12
			ft-lb/in	2.2
		3.2 mm, 23°C	Kg-cm/cm	14
			ft-lb/in	2.6
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	97
			°F	207
熱變形溫度 Heat Distortion Temp.	D648	1.8 MPa Annealed	°C	92
			°F	198
		1.8 MPa Unannealed	°C	78
			°F	174
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm V-0 1.5 mm 5VB 2.5 mm 5VA

