

General ABS POLYLAC® Characteristics PA-757

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	通用級 GENERAL
				PA-757
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	1.6
		220 °C, 10 Kg		-
比重 Mass Density	D792	23 °C	-	1.05
硬度 Hardness	D785	-	R Scale	116
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	470
			lb/in ²	6660
延伸率 Tensile Elongation	D638	6 mm/min	%	25
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	790
			lb/in ²	11660
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.7
			10 ⁵ lb/in ²	3.8
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	20
			ft-lb/in	3.7
		3.2 mm, 23°C	Kg-cm/cm	21
			ft-lb/in	3.9
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	105
			°F	221
熱變形溫度 Heat Distortion Temp.	D648	1.8 MPa Annealed	°C	95
			°F	203
		1.8 MPa Unannealed	°C	85
			°F	186
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

