

MABS POLYLAC® Characteristics PA-758R

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	一般級 GENERAL
				PA-758R
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	2.2
		220 °C, 10 Kg		-
比重 Mass Density	D792	23 °C	-	1.08
硬度 Hardness	D785	-	R Scale	110
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	420
			lb/in ²	5720
延伸率 Tensile Elongation	D638	6 mm/min	%	65
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	610
			lb/in ²	8650
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.1
			10 ⁵ lb/in ²	3.0
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	16
			ft-lb/in	3.0
		3.2 mm, 23°C	Kg-cm/cm	15
			ft-lb/in	2.8
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	102
			°F	216
熱變形溫度 Heat Distortion Temp.	D648	1.8 MPa Annealed	°C	97
			°F	207
		1.8 MPa Unannealed	°C	86
			°F	187
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

