

Flame Retardant ABS POLYLAC® Characteristics PA-765

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	防火級 FLAME RETARDANT
				PA-765
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	5.0
		220 °C, 10 Kg		-
比重 Mass Density	D792	23 °C	-	1.19
硬度 Hardness	D785	-	R Scale	100
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	390
			lb/in ²	5530
延伸率 Tensile Elongation	D638	6 mm/min	%	15
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	620
			lb/in ²	8800
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.1
			10 ⁵ lb/in ²	3.0
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	18
			ft-lb/in	3.3
		3.2 mm, 23°C	Kg-cm/cm	22
			ft-lb/in	4.0
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	90
			°F	194
熱變形溫度 Heat Distortion Temp.	D648	1.8 MPa Annealed	°C	83
			°F	181
		1.8 MPa Unannealed	°C	73
			°F	163
UL 燃燒等級 UL Flammability	UL 94	-	-	1.0 mm V-1 1.5 mm V-0 1.5 mm 5VB 2.5 mm 5VA

