

General PS POLYREX[®] Characteristics PG-33

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	通用級 GENERAL
				PG-33
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	8.0
比重 Mass Density	D792	23 °C	-	1.05
硬度 Hardness	D785	-	M Scale	77
拉伸強度 (斷裂) Tensile Strength (Break)	D638	6 mm/min	Kg/cm ²	460
			lb/in ²	6530
延伸率 Tensile Elongation	D638	6 mm/min	%	2
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	670
			lb/in ²	9510
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	3.1
			10 ⁵ lb/in ²	4.4
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	1.6
			ft-lb/in	0.29
		3.2 mm, 23°C	Kg-cm/cm	1.7
			ft-lb/in	0.31
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	94
			°F	201
熱變形溫度 Heat Distortion Temp.	D648	Annealed	°C	87
			°F	189
		Unannealed	°C	79
			°F	174
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

