

High Impact PS POLYREX® Characteristics PH-60

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	耐衝擊級 HIGH IMPACT
				PH-60
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	5.5
比重 Mass Density	D792	23 °C	-	1.05
硬度 Hardness	D785	-	L Scale	75
拉伸強度 (斷裂) Tensile Strength (Break)	D638	6 mm/min	Kg/cm ²	290
			lb/in ²	4120
延伸率 Tensile Elongation	D638	6 mm/min	%	40
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	430
			lb/in ²	6110
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.2
			10 ⁵ lb/in ²	3.1
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	7.5
			ft-lb/in	1.38
		3.2 mm, 23°C	Kg-cm/cm	8.5
			ft-lb/in	1.56
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	100
			°F	212
熱變形溫度 Heat Distortion Temp.	D648	Annealed	°C	96
			°F	205
		Unannealed	°C	81
			°F	178
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

