

General PC WONDERLITE® Characteristics PC-115

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	通用級 GENERAL
				PC-115
熔融指數 Melt Flow Index	D1238	300 °C, 1.2 Kg	g/10 min	15.0
比重 Mass Density	D792	23 °C	-	1.2
硬度 Hardness	D785	-	M Scale	77
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	630
			lb/in ²	8935
延伸率 Tensile Elongation	D638	6 mm/min	%	110
彎曲強度 Flexural Strength	D790	1.3 mm/min	Kg/cm ²	920
			lb/in ²	13030
彎曲彈性模數 Flexural Modulus	D790	1.3 mm/min	10 ⁴ Kg/cm ²	2.4
			10 ⁵ lb/in ²	3.4
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	3.2 mm, 23°C	Kg-cm/cm	87
			ft-lb/in	15.9
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	150
			°F	302
熱變形溫度 Heat Distortion Temp.	D648	Unannealed	°C	125
			°F	257
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm V-2

