

General SAN KIBISAN® Characteristics PN-127H

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	通用級 GENERAL
				PN-127H
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	1.5
比重 Mass Density	D792	23 °C	-	1.06
硬度 Hardness	D785	-	M Scale	85
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	780
			lb/in ²	11100
延伸率 Tensile Elongation	D638	6 mm/min	%	6
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	1100
			lb/in ²	15600
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	3.7
			10 ⁵ lb/in ²	5.2
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	1.9
			ft-lb/in	0.35
		3.2 mm, 23°C	Kg-cm/cm	2.2
			ft-lb/in	0.42
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	107
			°F	224
熱變形溫度 Heat Distortion Temp.	D648	Annealed	°C	103
			°F	217
		Unannealed	°C	94
			°F	201
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

