



Makrolon® 1095

Glass fiber (Normal fiber) reinforced grades / 15 % Glass fiber reinforced MVR (300 °C/1.2 kg) 6.0 cm³/10 min; 15 % glass fiber reinforced; UL 94V-0/3.0 mm; high viscosity; easy release; injection molding - melt temperature 310 - 330 °C; extrusion; available in opaque colors only; housings for power tools

ISO Shortname PC-GF15

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	300 °C/ 1.2 kg	cm³/10 min	ISO 1133	6.0
Melt mass-flow rate	300 °C/ 1.2 kg	g/10 min	ISO 1133	7.0
C Molding shrinkage, parallel	60x60x2 mm/ 500 bar	%	ISO 294-4	0.45
C Molding shrinkage, normal	60x60x2 mm/ 500 bar	%	ISO 294-4	0.45
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	4600
Yield stress	5 mm/min	MPa	ISO 527-1,-2	64
Yield strain	5 mm/min	%	ISO 527-1,-2	4.6
C Stress at break	5 mm/min	MPa	ISO 527-1,-2	45
C Strain at break	5 mm/min	%	ISO 527-1,-2	12
Flexural modulus	2 mm/min	MPa	ISO 178	4400
Flexural strength	2 mm/min	MPa	ISO 178	105
Flexural strain at flexural strength	2 mm/min	%	ISO 178	5.8
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	95
C Charpy impact strength	23 °C	kJ/m²	ISO 179/1eU	120C
Charpy impact strength	-60 °C	kJ/m²	ISO 179/1eU	90C
Charpy notched impact strength	23 °C/ 3 mm	kJ/m²	ISO 21305/based on ISO 179/1eA	10C
Izod notched impact strength	23 °C/ 3 mm	kJ/m²	ISO 21305/based on ISO 180/A	10C
C Puncture impact properties - maximum force	23 °C	N	ISO 6603-2	3600
C Puncture impact properties - maximum force	-30 °C	N	ISO 6603-2	3000
C Puncture energy	23 °C	J	ISO 6603-2	25
C Puncture energy	-30 °C	J	ISO 6603-2	13
Ball indentation hardness		N/mm²	ISO 2039-1	129



Makrolon® 1095

Property	Test Condition	Unit	Standard	typical Value
Thermal properties				
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	135
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	141
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	142
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	145
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.35
C Coefficient of linear thermal expansion, normal	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Burning behavior UL 94 (1.5 mm) [UL recognition]	1.5 mm	Class	UL 94	V-2
C Burning behavior UL 94 [UL recognition]	3.0 mm	Class	UL 94	V-0
C Oxygen index	Method A	%	ISO 4589-2	27
Resistance to heat (ball pressure test)		°C	IEC 60695-10-2	136
Relative temperature index (Tensile strength) [UL recognition]	1.5 mm	°C	UL 746B	80
Relative temperature index (Tensile impact strength) [UL recognition]	1.5 mm	°C	UL 746B	80
Relative temperature index (Electric strength) [UL recognition]	1.5 mm	°C	UL 746B	80
Glow wire test (GWFI)	0.75 mm	°C	IEC 60695-2-12	850
Glow wire test (GWFI)	1.5 mm	°C	IEC 60695-2-12	960
Glow wire test (GWFI)	3.0 mm	°C	IEC 60695-2-12	960
Glow wire test (GWIT)	0.75 mm	°C	IEC 60695-2-13	850
Glow wire test (GWIT)	1.5 mm	°C	IEC 60695-2-13	900
Glow wire test (GWIT)	3.0 mm	°C	IEC 60695-2-13	900
Needle flame test	Method K/ 1.5 mm	s	IEC 60695-11-5	60
Needle flame test	Method K/ 2.0 mm	s	IEC 60695-11-5	60
Needle flame test	Method K/ 3.0 mm	s	IEC 60695-11-5	120
Needle flame test	Method F/ 1.5 mm	s	IEC 60695-11-5	120
Needle flame test	Method F/ 2.0 mm	s	IEC 60695-11-5	120
Needle flame test	Method F/ 3.0 mm	s	IEC 60695-11-5	120
Burning rate (US-FMVSS)	>=1.0 mm	mm/min	ISO 3795	passed
Flash ignition temperature		°C	ASTM D1929	470
Self ignition temperature		°C	ASTM D1929	550
Electrical properties (23 °C/50 % r. h.)				
C Relative permittivity	100 Hz	-	IEC 60250	3.2
C Relative permittivity	1 MHz	-	IEC 60250	3.2
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	10
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	90
C Volume resistivity		Ohm·m	IEC 60093	1E14
C Surface resistivity		Ohm	IEC 60093	1E16
C Electrical strength	1 mm	kV/mm	IEC 60243-1	38
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	175
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	125M
Electrolytic corrosion		Rating	IEC 60426	A1
Other properties (23 °C)				
C Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.24
C Water absorption (equilibrium value)	23 °C; 50 % r. h.	%	ISO 62	0.10
C Density		kg/m³	ISO 1183-1	1290
Glass fiber content	Method A	%	b.o. ISO 3451-1	15
Bulk density	Pellets	kg/m³	ISO 60	640
Processing conditions for test specimens				
C Injection molding - Melt temperature		°C	ISO 294	300
C Injection molding - Mold temperature		°C	ISO 294	110
C Injection molding - Injection velocity		mm/s	ISO 294	200





Makrolon® 1095

Property	Test Condition	Unit	Standard	typical Value
Recommended processing and drying conditions				
Melt temperatures		°C	-	310 - 330
Standard Melt temperature		°C	-	320
Barrel Temperatures - Rear		°C	-	260 - 270
Barrel Temperatures - Middle		°C	-	280 - 290
Barrel Temperatures - Front		°C	-	300 - 310
Barrel Temperatures - Nozzle		°C	-	310 - 320
Mold Temperatures		°C	-	80 - 130
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	120
Dry Air Drying Time		h	-	2-3
Moisture Content max. (%)		%	-	<= 0,02
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

