



Makrolon® ET UV112

Grades / Extrusion

MVR (300 °C/1.2 kg) 13 cm³/10 min; high viscosity; Corrugated Sheets; special grade for the coextrusion of Makrolon ET base resins; with anti stick properties for finished sheets; available in color code 551340 only

ISO Shortname

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
Melt volume-flow rate	300 °C/ 1.2 kg	cm³/10 min	ISO 1133	13
Other properties (23 °C)				
C Density		kg/m³	ISO 1183-1	1200

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

