



Makroblend® UT1018

/ (PET+PC) blend, unreinforced; impact modified, injection molding grade. Good dimensional stability; excellent low-temperature impact and chemical resistance. UL746C f2 rated.

ISO Shortname

PC+PET-I

Property	Test Condition	Unit	Standard	typical Value
Rheological properties				
C Melt volume-flow rate	270 °C/ 5 kg	cm³/10 min	ISO 1133	13
Molding shrinkage, parallel/normal	Value range based on general practical experience (600bar)	%	b.o. ISO 2577	0.7 - 0.9
Mechanical properties (23 °C/50 % r. h.)				
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2000
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	49
C Yield strain	50 mm/min	%	ISO 527-1,-2	4.5
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	100
Stress at break	50 mm/min	MPa	ISO 527-1,-2	46
Flexural modulus	2 mm/min	MPa	ISO 178	1900
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	60
Flexural strength	2 mm/min	MPa	ISO 178	70
C Charpy notched impact strength	23 °C	kJ/m²	ISO 179/1eA	65
C Charpy notched impact strength	-30 °C	kJ/m²	ISO 179/1eA	35
Izod notched impact strength	23 °C	kJ/m²	ISO 180/A	60
Izod notched impact strength	-20 °C	kJ/m²	ISO 180/A	50
Thermal properties				
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	78
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	108
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	132
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.8
C Coefficient of linear thermal expansion, normal	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.9
C Burning behavior UL 94 (1.5 mm) [UL recognition]		Class	UL 94	HB
C Burning behavior UL 94 [UL recognition]	3.0 mm	Class	UL 94	HB
Thermal conductivity, through-plane	23 °C; 50 % r. h.	W/(m·K)	ISO 8302	0.2
Electrical properties (23 °C/50 % r. h.)				
C Relative permittivity	100 Hz	-	IEC 60250	3.2
C Relative permittivity	1 MHz	-	IEC 60250	3.1
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	20
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	150
C Volume resistivity		Ohm·m	IEC 60093	1E14
C Surface resistivity		Ohm	IEC 60093	1E16
C Electrical strength	1 mm	kV/mm	IEC 60243-1	34
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	600
Other properties (23 °C)				
C Water absorption (saturation value)	Water at 23 °C	%	ISO 62	0.7
C Water absorption (equilibrium value)	23 °C; 50 % r. h.	%	ISO 62	0.2
C Density		kg/m³	ISO 1183-1	1220
Processing conditions for test specimens				
C Injection molding - Melt temperature		°C	ISO 294	270
C Injection molding - Mold temperature		°C	ISO 294	70
C Injection molding - Injection velocity		mm/s	ISO 294	200





Makroblend® UT1018

Property	Test Condition	Unit	Standard	typical Value
Recommended processing and drying conditions				
Melt temperatures		°C	-	260 - 280
Standard Melt temperature		°C	-	270
Barrel Temperatures - Rear		°C	-	245 - 255
Barrel Temperatures - Middle		°C	-	250 - 260
Barrel Temperatures - Front		°C	-	255 - 265
Barrel Temperatures - Nozzle		°C	-	255 - 270
Mold Temperatures		°C	-	50 - 100
Hold Pressure (% of injection pressure)		%	-	50 - 75
Plastic Back Pressure (specific)		bar	-	50 - 150
Peripheral Screw Speed		m/s	-	0.05 - 0.2
Shot-to-Cylinder Size		%	-	30 - 70
Dry Air Drying Temperature		°C	-	110
Dry Air Drying Time		h	-	2-4
Moisture Content max. (%)		%	-	<= 0,01
Vent Depth		mm	-	0.025 - 0.075

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break

