



Desmopan 3072D

300 品级系列, 酯类 / 邵氏硬度 D 70 - 74

injection molding grade; high mechanical strength; excellent abrasion resistance; good wear resistance; very short cycle times; Application; Technical parts

ARES

性能	测试条件	单位	标准	数值		
				drying	annealed	-
				according to specifications		
机械性能						
C 邵氏硬度 A	1s	-	DIN ISO 7619-1		98	
C 邵氏硬度 D	1s	-	DIN ISO 7619-1		72	
C 最终拉伸强度	200 mm/min	MPa	DIN 53504		60	
C 断裂应变	200 mm/min	%	DIN 53504		350	
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504		34	
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504		52	
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A		49	
C 压缩率	72 h; 23 ° C	%	DIN ISO 815-1		29	
C 耐磨性		mm³	ISO 4649 method A		20	
C 回弹力		%	ISO 4662		47	
C 撕裂强度	500 mm/min	kN/m	ISO 34-1		256	
C 弯曲模量	2 mm/min	MPa	ISO 178		800	
热性质						
C 拉伸储能模量	-20 ° C	MPa	ISO 6721-1, -4		3330	
C 拉伸储能模量	20 ° C	MPa	ISO 6721-1, -4		1275	
C 拉伸储能模量	60 ° C	MPa	ISO 6721-1, -4		385	
其他性能 (23 ° C)						
C 密度		kg/m³	ISO 1183-1			1240
建议成型工艺参数说明:						
C 注塑-熔体温度		°C	-	225 - 245		
C 注塑-模具温度		°C	-			60 - 80
C Maximum drying temperature		°C	-			110

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则

