



Desmopan 6080A

600 品级系列, 醚类 / 邵氏硬度 A 80 - 84

injection molding grade; free from plasticizers; easy flowing; very good hydrolysis and microbial resistance; low abrasion; short cycle times; Cylindrical pellets; automotive interior applications; hard - soft systems; Shoe soles

ARET

性能	测试条件	单位	标准	数值		
drying annealed - according to specifications						
机械性能						
C 邵氏硬度 A	1s	-	DIN ISO 7619-1		80	
C 最终拉伸强度	200 mm/min	MPa	DIN 53504		28	
C 断裂应变	200 mm/min	%	DIN 53504		667	
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504		5, 6	
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504		10, 1	
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A		38	
C 压缩率	72 h; 23 ° C	%	DIN ISO 815-1		18	
C 耐磨性		mm³	ISO 4649 method A		43	
C 回弹力		%	ISO 4662		43	
C 撕裂强度	500 mm/min	kN/m	ISO 34-1		36	
热性质						
C 拉伸储能模量	20 ° C	MPa	ISO 6721-1, -4		21	
C 拉伸储能模量	60 ° C	MPa	ISO 6721-1, -4		13	
其他性能 (23 ° C)						
C 密度		kg/m³	ISO 1183-1			1110
建议成型工艺参数说明:						
C 注塑-熔体温度		°C	-	200 - 220		
C 注塑-模具温度		°C	-			20

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则



ISO 特性表

