



Desmopan 6580A MVT

/ Extrusion grade; very good hydrolysis and microbial resistance; high moisture vapor transmission rate;
Application; breathable films; Textile coating
ARET

性能	测试条件	单位	标准	数值
				drying annealed - according to specifications

机械性能						
C 邵氏硬度 A	1s	-	DIN ISO 7619-1		79	
C 最终拉伸强度	200 mm/min	MPa	DIN 53504		30	
C 断裂应变	200 mm/min	%	DIN 53504		850	
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504		4	
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504		7	

建议成型工艺参数说明:						
C Drying Temperature		°C	-			80-110

C 这些性能数据来源於 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则

