



Makroblend UT 403

Impact modified grades / General purpose

UV-stabilized, high-flow, impact-modified polycarbonate/PET polyester blend with UL 746C approval

ISO Shortname

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Spiral flow length	0.100 in, 525 °F melt temperature	in	Bayer test	28
Mold shrinkage, flow/cross to flow		in/in	ASTM D 955	0.006-0.008
Melt flow rate	265 °C; 5 kg	g/(10 min)	ASTM D 1238	24 - 34
Mechanical properties (23 °C/50 % r.h.)				
Tensile stress at yield		lb/in ²	ASTM D 638	8100
Tensile elongation at yield		%	ASTM D 638	5.0
Tensile elongation at break		%	ASTM D 638	151
Tensile stress at break		lb/in ²	ASTM D 638	8000
Izod notched impact strength	73 °F; 0.125 in	ft-lb/in	ASTM D 256	15
Izod notched impact strength	-20 °F; 0.125 in	ft-lb/in	ASTM D 256	3
Izod notched impact strength	-40 °F; 0.125 in	ft-lb/in	ASTM D 256	2
Izod notched impact strength	73 °F; 0.250 in	ft-lb/in	ASTM D 256	4.0
Flexural modulus	-	lb/in ²	ASTM D 790	338000
Flexural stress at 5 % strain		lb/in ²	ASTM D 790	12400
Instrumented impact, Total energy	73 °F; 0.125 in; 0.5-in dart; 3-in clamp; 7.6 mph	ft-lb	ASTM D 3763	41
Instrumented impact, Total energy	-20 °F; 0.125 in; 0.5-in dart; 3-in clamp; 15 mph	ft-lb	ASTM D 3763	42
Instrumented impact, Total energy	-40 °F; 0.125 in; 0.5-in dart; 3-in clamp; 7.6 mph	ft-lb	ASTM D 3763	41
Rockwell hardness		R Scale	ASTM D 785	121
Thermal properties				
Deflection temperature under load, Unannealed	264 psi; 0.250 in	°F	ASTM D 648	248
Deflection temperature under load, Unannealed	66 psi; 0.250 in	°F	ASTM D 648	273
Coefficient of linear thermal expansion, flow/cross-flow		in/in/°F	ASTM D 696	3.7E-05
UL94 Flame Class	Thickness tested: 1.5 mm	Class	UL 94	HB
UL94 Flame Class	Thickness tested: 3.0 mm	Class	UL 94	HB
Relative temperature index, mechanical with impact	Thickness tested: 1.5 mm	°C	UL 746 B	75
Relative temperature index, electrical	Thickness tested: 1.5 mm	°C	UL 746 B	75
Relative temperature index, mechanical without impact	Thickness tested: 1.5 mm	°C	UL 746 B	75
Electrical properties (23 °C/50 % r.h.)				
Dissipation factor, Tinfoil electrodes	1 MHz	-	ASTM D 150	0.009
Volume resistivity, Tinfoil electrodes		Ohm-m	ASTM D 257	>7.4E15
Dielectric strength	Short time under oil at 73 °F	V/mil	ASTM D 149	704
Other properties (23 °C)				
Water absorption	73 °F; immersion to saturation	%	ASTM D 570	0.25
Water absorption	73 °F; immersion 24 h	%	ASTM D 570	0.11
Specific volume		in ³ /lb	ASTM D 792	22.7
Density		lb/in ³	ASTM D 792	0.044

