



LNP™ LUBRICOMP™ Compound ECL36

Americas: COMMERCIAL

Also known as: LNP™ LUBRICOMP™ Compound ECL-4036

Product reorder name: ECL36

LNP* LUBRICOMP* ECL36 is a compound based on Polyetherimide resin containing 30% Carbon Fiber, 15% PTFE. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1820	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.7	%	ASTM D 638
Flexural Stress	2350	kgf/cm ²	ASTM D 790
Flexural Modulus	195400	kgf/cm ²	ASTM D 790
Tensile Stress, break	160	MPa	ISO 527
Tensile Strain, break	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	21600	MPa	ISO 527
Flexural Stress	210	MPa	ISO 178
Flexural Modulus	16000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	27	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	4	cm-kgf/cm	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	18	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	208	°C	ASTM D 648
PHYSICAL			
Density	1.48	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.04	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.4	%	ASTM D 955
Wear Factor Washer	31	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.39	-	ASTM D 3702 Modified: Manual
Static COF	0.48	-	ASTM D 3702 Modified: Manual
Density	1.5	g/cm ³	ISO 1183





LNP™ LUBRICOMP™ Compound ECL36

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
ELECTRICAL Surface Resistivity	1.E+01 - 1.E+06	Ohm	ASTM D 257





LNP™ LUBRICOMP™ Compound ECL36

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	360 - 365	°C
Front - Zone 3 Temperature	365 - 375	°C
Middle - Zone 2 Temperature	355 - 365	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	120 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm

