



LNP™ THERMOCOMP™ Compound PDXE98480

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound PDX-E-98480 PS

Product reorder name: PDXE98480

LNP THERMOCOMP PDXE98480 is a compound based on Polyetherimide with Proprietary Fillers. Added feature of this grade: Reinforced.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	1830	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	153900	kgf/cm ²	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	2590	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	136600	kgf/cm ²	ASTM D 790
Tensile Stress, break, 5 mm/min	162	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	14220	MPa	ISO 527
Flexural Stress	243	MPa	ISO 178
Flexural Modulus, 2 mm/min	12790	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	50	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	9	cm-kgf/cm	ASTM D 256
Multiaxial Impact	40	cm-kgf	ISO 6603
Instrumented Impact Total Energy, 23°C	122	cm-kgf	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	33	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	213	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	208	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.9E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	9.2E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	213	°C	ISO 75/Bf





LNP™ THERMOCOMP™ Compound PDXE98480

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	208	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.6	-	ASTM D 792
Density	1.6	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.12	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2 - 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.4 - 0.6	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.17	%	ISO 62





LNP™ THERMOCOMP™ Compound PDXE98480

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4 - 6	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	360 - 365	°C
Front - Zone 3 Temperature	365 - 375	°C
Middle - Zone 2 Temperature	355 - 365	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	120 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm

