



ULTEM™ Resin DU242
Americas: COMMERCIAL

Enhanced low temperature impact, high flow Polyetherimide blend. ECO Conforming.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	750	kgf/cm ²	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	67	%	ASTM D 638
Tensile Modulus, 5 mm/min	26300	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	1140	kgf/cm ²	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	25600	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	18	cm-kgf/cm	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	208	cm-kgf/cm	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	160	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.24	-	ASTM D 792
Melt Flow Rate, 337°C/6.6 kgf	30	g/10 min	ASTM D 1238





ULTEM™ Resin DU242
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	135	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	12	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	330 - 355	°C
Nozzle Temperature	325 - 350	°C
Front - Zone 3 Temperature	330 - 355	°C
Middle - Zone 2 Temperature	320 - 345	°C
Rear - Zone 1 Temperature	310 - 330	°C
Mold Temperature	95 - 135	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm

