



ULTEM™ Resin LTX300A
Americas: COMMERCIAL

High flow Polyetherimide blend with low toxicity, smoke and flame evolution. ECO Compliant, UL94 V0 listing in recognized colors.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	980	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	860	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	30	%	ASTM D 638
Tensile Modulus, 5 mm/min	33700	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	1470	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	33000	kgf/cm ²	ASTM D 790
Taber Abrasion, CS-17, 1 kg	15	mg/1000cy	SABIC Method
Tensile Stress, yield, 5 mm/min	90	MPa	ISO 527
Tensile Stress, break, 5 mm/min	75	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	25	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Modulus, 2 mm/min	3200	MPa	ISO 178
Hardness, H358/30	127	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched, 23°C	214	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	7	cm-kgf/cm	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	212	cm-kgf/cm	ASTM D 256
Gardner, 23°C	356	cm-kgf	ASTM D 3029
Instrumented Impact Total Energy, 23°C	407	cm-kgf	ASTM D 3763





ULTEM™ Resin LTX300A
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	210	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	201	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	187	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	204	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	189	°C	ASTM D 648
CTE, -40°C to 150°C, flow	5.E-05	1/°C	ASTM E 831
CTE, -40°C to 150°C, xflow	5.E-05	1/°C	ASTM E 831
Thermal Conductivity	0.26	W/m·°C	ISO 8302
CTE, 23°C to 150°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	5.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Passes	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	210	°C	ISO 306
Vicat Softening Temp, Rate B/50	200	°C	ISO 306
Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	200	°C	ISO 75/Be





ULTEM™ Resin LTX300A

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	185	°C	ISO 75/Ae
PHYSICAL			
Specific Gravity	1.3	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.6 - 0.8	%	SABIC Method
Mold Shrinkage, flow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm (5)	0.5 - 0.7	%	SABIC Method
Melt Flow Rate, 295°C/6.6 kgf	2.4	g/10 min	ASTM D 1238
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	1.25	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62
Melt Volume Rate, MVR at 340°C/5.0 kg	15	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	0.75	mm	UL 94 by SABIC-IP





ULTEM™ Resin LTX300A
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	135	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	10	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	350 - 370	°C
Nozzle Temperature	350 - 370	°C
Front - Zone 3 Temperature	350 - 370	°C
Middle - Zone 2 Temperature	345 - 365	°C
Rear - Zone 1 Temperature	340 - 360	°C
Mold Temperature	135 - 165	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	40 - 70	rpm
Shot to Cylinder Size	40 - 60	%
Vent Depth	0.025 - 0.076	mm

