



LNP™ THERMOCOMP™ Compound JF004RXP

Europe-Africa-Middle East: COMMERCIAL

LNP THERMOCOMP JF004RXP is a compound based on Polyethersulfone resin containing Glass Fiber.
Added features of this material include: Mold Release.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break, 5 mm/min	122	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	7100	MPa	ISO 527
Flexural Modulus, 2 mm/min	6000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	223	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	219	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.25 - 0.45	%	SABIC Method
Density	1.52	g/cm ³	ISO 1183
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating (3)(4)	0.8	mm	UL 94 by SABIC-IP
UL Recognized, 94V-0 Flame Class Rating (3)	0.8	mm	UL 94





LNP™ THERMOCOMP™ Compound JF004RXP

Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	355 - 370	°C
Front - Zone 3 Temperature	370 - 380	°C
Middle - Zone 2 Temperature	360 - 370	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	140 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm

