



LNP™ THERMOCOMP™ Compound JF006LZZ

Americas: COMMERCIAL

Also known as: LNP™ THERMOCOMP™ Compound JF-1006 E LE

Product reorder name: JF006LZZ

LNP THERMOCOMP™ JF006LZZ is a compound based on Polyethersulfone resin containing 30% Glass Fiber. Added features of this material include:
Extrusion Grade, Low Extractable.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, break	1150	kgf/cm ²	ASTM D 638
Tensile Strain, break	1.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	99800	kgf/cm ²	ASTM D 638
Flexural Stress	1810	kgf/cm ²	ASTM D 790
Flexural Modulus	94200	kgf/cm ²	ASTM D 790
Tensile Stress, break	99	MPa	ISO 527
Tensile Strain, break	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	10190	MPa	ISO 527
Flexural Stress	222	MPa	ISO 178
Flexural Modulus	9240	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	44	cm-kgf/cm	ASTM D 4812
Izod Impact, notched, 23°C	5	cm-kgf/cm	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	130	cm-kgf	ASTM D 3763
Multiaxial Impact	27	cm-kgf	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	29	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	217	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	212	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	3.63E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.01E-05	1/°C	ISO 11359-2





LNP™ THERMOCOMP™ Compound JF006LZZ

Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
THERMAL			
CTE, -40°C to 40°C, xflow	3.64E-05	1/°C	ISO 11359-2
PHYSICAL			
Density	1.613	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.36	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.7	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.25	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.69	%	ISO 294
Density	1.6	g/cm³	ISO 1183





LNP™ THERMOCOMP™ Compound JF006LZZ

Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	120 - 150	°C
Drying Time	4	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	355 - 370	°C
Front - Zone 3 Temperature	370 - 380	°C
Middle - Zone 2 Temperature	360 - 370	°C
Rear - Zone 1 Temperature	345 - 355	°C
Mold Temperature	140 - 150	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	60 - 100	rpm

