



LNP™ LUBRICOMP™ Compound ML008
Europe-Africa-Middle East: COMMERCIAL

LNP LUBRICOMP ML008 is a compound based on Polypropylene resin containing PTFE. Added Features include: Internally Lubricated.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	Unit	Standard
MECHANICAL			
Tensile Stress, yield, 5 mm/min	23	MPa	ISO 527
Tensile Strain, break, 5 mm/min	19.6	%	ISO 527
Tensile Modulus, 1 mm/min	1300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	40	MPa	ISO 178
Flexural Modulus, 2 mm/min	1600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	1.28E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.35E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	114	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	68	°C	ISO 75/Af
PHYSICAL			
Mold Shrinkage, flow (5)	2	%	SABIC Method
Density	1.19	g/cm ³	ISO 1183





LNP™ LUBRICOMP™ Compound ML008
Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	Unit
Injection Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Melt Temperature	225 - 250	°C
Front - Zone 3 Temperature	240 - 250	°C
Middle - Zone 2 Temperature	215 - 225	°C
Rear - Zone 1 Temperature	195 - 205	°C
Mold Temperature	30 - 50	°C
Back Pressure	0.2 - 0.3	MPa
Screw Speed	30 - 60	rpm

