

SABIC® PPCOMPOUND 2609B

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

 $SABIC^{\circledR} PP compound\ 2609B\ is\ a\ mineral\ filled\ modified\ polypropylene.\ Typical\ material\ properties\ include\ good\ stiffness\ and\ impact.\ Typical\ applications\ include\ automotive\ exterior\ trims\ such\ as\ lateral\ siding.\ It\ can\ be\ used\ in\ painted\ and\ unpainted\ applications.$

 $\mathsf{SABIC}^{\circledR} \ \mathsf{PPcompound} \ 2609 \mathsf{B} \ \mathsf{is} \ \mathsf{a} \ \mathsf{designated} \ \mathsf{automotive} \ \mathsf{grade}.$

IMDS ID: 554796047

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|------------------------------------|----------------|--------|--------------|
| | | | |
| POLYMER PROPERTIES | | | |
| Melt flow rate (MFR) | | | |
| at 230 °C and 2.16 kg | 15 | dg/min | ISO 1133 |
| Density ⁽¹⁾ | 1120 | kg/m³ | ISO 1183 |
| Filler content | 27 | % | SABIC method |
| Mould shrinkage ⁽²⁾ | | | |
| 24 hours after injection moulding | 0.9 | % | SABIC method |
| MECHANICAL PROPERTIES (1) | | | |
| Tensile test | | | |
| Tensile modulus | 1250 | MPa | ISO 527/1A |
| stress at yield | 28 | MPa | ISO 527/1A |
| stress at break | 15 | MPa | ISO 527/1A |
| strain at break | 10 | % | ISO 527/1A |
| Flexural test | | | |
| Flexural modulus | 1300 | MPa | ISO 178/1A |
| Izod impact notched (3) | | | |
| at 23 °C | 25 | kJ/m² | ISO 180/1A |
| at 0 °C | 15 | kJ/m² | ISO 180/1A |
| at -20 °C | 5 | kJ/m² | ISO 180/1A |
| THERMAL PROPERTIES (1) | | | |
| Heat deflection temperature | | | |
| at 1.80 MPa (HDT/A) | - | °C | ISO 75 |
| at 0.45 MPa (HDT/B) | 105 | °C | ISO 75 |
| Coeff. of linear thermal expansion | | | |
| -30 °C to 100 °C | - | μm/mK | ISO 11359-2 |

- (1) Injection molded sample ISO527-1A
- (2) Injection molded plaque 65x65x3.2mm
- (3) N.B.: No Break



