

SABIC[®] PP 107M90T

POLYPROPYLENE IMPACT COPOLYMER
REGION ASIA

DESCRIPTION

SABIC[®] PP 107M90T is a medium fluidity polypropylene impact copolymer with super high impact strength. It contains antistatic agents.

TYPICAL APPLICATIONS

SABIC[®] PP 107M90T can be used for auto interior or exterior, home appliances parts, housewares and compounding.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 230°C and 2.16 kg	10	g/10 min	ISO 1133
Density	905	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile Strength at Yield	20	MPa	ASTM D638
Flexural Modulus (1% Secant)	900	MPa	ASTM D790 A
Charpy Impact Strength Notched ⁽¹⁾			
at 23 °C	50	kJ/m ²	ISO 179-1
at -20 °C	7	kJ/m ²	ISO 179-1
Rockwell Hardness			
R-scale	85	-	ISO 2039-2
THERMAL PROPERTIES			
Heat deflection temperature			
at 455kPa	75	°C	ISO 75-2

(1) Based on injection molded specimens.

