

SABIC® PP 37MK10R

PP IMPACT COPOLYMER

DESCRIPTION

SABIC® PP 37MK10R is an impact copolymer polypropylene resin and is typically used for industrial injection molding application. Molded parts made from this resin typically exhibits good impact, high stiffness and good heat stability.

TYPICAL APPLICATIONS

Crates, electrical appliances, thin wall applications and industrial applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
@ 230°C / 2.16 kg	9	g / 10 min	ASTM D1238
MECHANICAL PROPERTIES			
Tensile Strength at Yield	28	MPa	ASTM D638
Tensile Strength at Break	15	MPa	ASTM D638
Flexural Modulus (1% Secant)	1530	MPa	ASTM D790 A
Izod Impact Strength			
Notched, 23°C	10	kJ / m ²	ISO 180
Notched, -20°C	5	kJ / m ²	ISO 180
Rockwell Hardness, R-Scale	96	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Point	153	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	124	°C	ASTM D648

