

# SABIC® PP 505P

PP HOMOPOLYMER

## DESCRIPTION

SABIC® PP 505P is a low mfi grade typically used in extrusion applications like sheet and thermoforming.

Application:SABIC® PP 505P is typically used in dairy, flower pots, yellow fats and disposables plates and cups. However, customers use this grade also in combination with fillers like Talc and CaCO<sub>3</sub>.

Health, Safety and Food Contact regulations:Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	2.0	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>Molecular Weight Distribution</b>	Broad	-	-
<b>Isotacticity</b>	Medium	-	-
<b>FORMULATION</b>			
<b>Anti static agent</b>	<input type="checkbox"/>	-	-
<b>Nucleating agent</b>	<input type="checkbox"/>	-	-
<b>Gas fading stabilized</b>	<input type="checkbox"/>	-	SABIC method
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
strain at yield <sup>(1)</sup>	10	%	ISO 527-2 1A
stress at yield	37	MPa	ISO 527-2 1A
tensile modulus <sup>(2)</sup>	1500	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 23 °C	3.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	4.5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature <sup>(3)</sup></b>			
at 0.45 MPa (HDT/B)	85	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
<b>Vicat Softening Temperature <sup>(4)</sup></b>			
at 10 N (VST/A)	152	°C	ISO 306
at 50 N (VST/B)	88	°C	ISO 306

(1) Speed of testing: 50 mm/min

(2) Speed of testing: 1 mm/min

(3) Flat wise ( testbar 80\*10\*4mm)

(4) Temperature rate: 120°C/h

