

# SABIC® PP 46MNK45

PP IMPACT COPOLYMER

## DESCRIPTION

SABIC® 46MNK45 is a phthalate free polypropylene impact copolymer grade suitable for both injection and compression molding of beverage closures. The main features of this grade are very good processability, good stiffness and impact resistance. This is a nucleated grade with slip and antistatic agent.

## TYPICAL APPLICATIONS

SABIC® 46MNK45 can be used for production of beverage closures, housewares and industrial packaging etc.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Modulus, 50 mm/min	1500	MPa	ASTM D638
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
@ 230°C & 2.16 kg load	6	g/10 min	ASTM D1238
<b>Density</b>			
@ 23°C	905	kg/m³	ASTM D792
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile strength</b>			
@ Yield	30	MPa	ASTM D638
<b>Tensile Elongation</b>			
@ Yield	7	%	ASTM D638
<b>Flexural Modulus</b>			
(1% Secant)	1400	MPa	ASTM D790 A
Notched Izod Impact Strength at 23°C	80	J/m	ASTM D256
Notched Izod Impact Strength at -20°C	27	J/m	ASTM D256
Rockwell Hardness, R-Scale	80	-	ASTM D785
<b>THERMAL PROPERTIES</b>			
Vicat Softening Point	149	°C	ASTM D1525
<b>Heat deflection temperature</b>			
@ 455 kPa	110	°C	ASTM D648

(1) Based on injection molded specimens

