

# SABIC<sup>®</sup> PPCOMPOUND 55T1040

PP COMPOUND MINERAL FILLED

## DESCRIPTION

SABIC<sup>®</sup> PPcompound 55T1040 is a general purpose, talc filled, heat stabilized copolymer polypropylene compound. This compound exhibits very high impact and high rigidity, and is suitable for injection molding applications.

IMDS ID: 278629571

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt flow rate (MFR)</b>			
at 230 °C and 2.16 kg	3	dg/min	ISO 1133
<b>Density</b> <sup>(1)</sup>	1270	kg/m <sup>3</sup>	ISO 1183
<b>Filler content</b>	40	%	SABIC method
<b>Mould shrinkage</b> <sup>(2)</sup>			
24 hours after injection moulding	-	%	SABIC method
<b>MECHANICAL PROPERTIES</b> <sup>(1)</sup>			
<b>Tensile</b>			
Tensile modulus	2450	MPa	ISO 527/1A
stress at yield	20	MPa	ISO 527/1A
stress at break	14	MPa	ISO 527/1A
strain at break	10.8	%	ISO 527/1A
<b>Flexural test</b>			
Flexural modulus	3270	MPa	ISO 178/1A
<b>Izod impact notched</b> <sup>(3)</sup>			
at 23 °C	7	kJ/m <sup>2</sup>	ISO 180/1A
at 0 °C	-	kJ/m <sup>2</sup>	ISO 180/1A
at -20 °C	2	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL PROPERTIES</b> <sup>(1)</sup>			
<b>Heat deflection temperature</b>			
at 1.80 Mpa (HDT/A)	70	°C	ISO 75
at 0.45 Mpa (HDT/B)	124	°C	ISO 75
<b>Coeff. of linear thermal expansion</b>			
-30 °C to 100 °C	-	µm/mK	ISO 11359-2

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

