

SABIC® PP 5704PR

POLYPROPYLENE HOMOPOLYMER

DESCRIPTION

SABIC® PP 5704PR is a homopolymer polypropylene resin and is typically used for injection molding and compounding applications. Product made from this resin typically exhibits high stiffness and good flow characteristic.

TYPICAL APPLICATIONS

General purpose, housewares. This product is not intended for use in medical and pharmaceutical applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
@ 230°C/2.16 kg	11	g/10 min	ASTM D1238
MECHANICAL PROPERTIES			
Tensile Strength at Yield	36	MPa	ASTM D638
Flexural Modulus (1% Secant)	1700	MPa	ASTM D790 A
Flexural Strength	44	MPa	ASTM D790
Izod Impact , Notched, 23 °C	2	kJ/m²	ISO 180
THERMAL PROPERTIES			
Heat Deflection Temperature at 455kPa	120	°C	ASTM D648



