

# SABIC® PP QR675K

PP RANDOM COPOLYMER QCRYSTAL

## DESCRIPTION

SABIC® PP QR675K is a highly transparent random copolymer with good antistatic properties with excellent flow behaviour. This grade combines improved aesthetics of the finished articles with low temperature processability. Part aesthetics are not affected by the lower processing temperatures, providing for a broader operating window. The SABIC® PP QR675K results in excellent demoulding characteristics and has a good stiffness to impact ratio.

Application: SABIC® PP QR675K is mainly used in injection moulding processes. The SABIC® PP QR675K aims at transparent applications where higher MFI's with good flow are required. Its intended applications include injection moulded housewares, office & home storage boxes, thin wall packaging and media packaging.

## TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	60	dg/min	ISO 1133
<b>Density</b>	905	kg/m³	ASTM D1505
<b>FORMULATION</b>			
Anti static agent	☑	-	-
Clarified	☑	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
stress at yield <sup>(1)</sup>	25	MPa	ISO 527-2 1A
strain at yield	13	%	ISO 527-2 1A
tensile modulus <sup>(2)</sup>	1100	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 0 °C	2.0	kJ/m²	ISO 180/1A
at 23 °C	4.0	kJ/m²	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	4.5	kJ/m²	ISO 179/1eA
at 0 °C	2.0	kJ/m²	ISO 179/1eA
<b>Hardness Shore D</b>	62	-	ISO 868
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature <sup>(3)</sup></b>			
at 1.80 MPa (HDT/A)	50	°C	ISO 75
at 0.45 MPa (HDT/B)	75	°C	ISO 75
<b>Vicat Softening Temperature <sup>(4)</sup></b>			



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
at 10 N (VST/A)	125	°C	ISO 306
at 50 N (VST/B)	68	°C	ISO 306

- (1) Speed of testing: 50 mm/min  
 (2) Speed of testing: 1 mm/min  
 (3) Flat wise ( testbar 80\*10\*4mm)  
 (4) Temperature rate: 120°C/h

