

SABIC® PP 95MK40T

POLYPROPYLENE IMPACT COPOLYMER
REGION ASIA

DESCRIPTION

SABIC® PP 95MK40T is a polypropylene impact copolymer with very high impact strength, high stiffness and high heat deflection temperature. It is specifically designed for applications that require high impact resistance and high top load strength at broad temperature range. It contains nucleating & antistatic agents.

TYPICAL APPLICATIONS

SABIC® PP 95MK40T is suitable for the production of industrial pail, yoghurt tub and other food contact applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
@230°C&2.16kg	3.5	g/10 min	ISO 1133
Density			
@23°C	905	kg/m³	ISO 1183
MECHANICAL PROPERTIES			
Tensile strength			
@Yield	23	MPa	ISO 527-2
Flexural Modulus			
(1% Secant)	1200	MPa	ISO 178
Charpy Impact Strength Notched			
@23°C	50	kJ/m²	ISO 179-1
@-20°C	6.5	kJ/m²	ISO 179-1
Rockwell Hardness			
R-Scale	95	-	ISO 2039-2
THERMAL PROPERTIES			
Heat deflection temperature			
@455kPa	90	°C	ISO 75-2

