

SABIC® PP PHC3 1

PP IMPACT COPOLYMER

DESCRIPTION

SABIC® PP PHC3 1 combines high stiffness with good impact strength. Its excellent flow properties and narrow molecular weight distribution allows fast cycle-times and injection moulding of articles demanding low warpage and high dimensional stability. Typical applications are pails, containers, crates & boxes and automotive components.

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	15	dg/min	ISO 1133
Density	905	kg/m³	ASTM D1505
FORMULATION			
Anti static agent	<input type="checkbox"/>	-	-
Nucleating agent	<input type="checkbox"/>	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	25	MPa	ISO 527-2 1A
tensile modulus ⁽¹⁾	1300	MPa	ISO 527-2 1A
strain at yield ⁽²⁾	5	%	ISO 527-2 1A
Izod impact notched			
at 0 °C	7	kJ/m²	ISO 180/1A
at 23 °C	11	kJ/m²	ISO 180/1A
at -20 °C	5	kJ/m²	ISO 180/1A
Charpy Impact Strength Notched			
at 0 °C	8	kJ/m²	ISO 179/1eA
at -20 °C	5	kJ/m²	ISO 179/1eA
at 23 °C	12.5	kJ/m²	ISO 179/1eA
Hardness Shore D	64	-	ISO 868
THERMAL PROPERTIES			
Heat deflection temperature ⁽³⁾			
at 1.80 MPa (HDT/A)	55	°C	ISO 75
at 0.45 MPa (HDT/B)	80	°C	ISO 75
Vicat Softening Temperature ⁽⁴⁾			
at 10 N (VST/A)	149	°C	ISO 306
at 50 N (VST/B)	74	°C	ISO 306

