

SABIC® PPCOMPOUND 2605

PP COMPOUND MINERAL FILLED IMPACT MODIFIED

DESCRIPTION

SABIC[®] PPcompound 2605 is a mineral filled modified polypropylene. Typical material properties include an excellent impact stiffness balance with a low density. Typical applications include automotive interior parts such as trims and dashboards.

SABIC® PPcompound 2605 is a designated automotive grade.

IMDS ID: 16485887

TYPICAL PROPERTY VALUES

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|------------------------------------|----------------|--------|--------------|
| POLYMER PROPERTIES | | | |
| Melt flow rate (MFR) | | | |
| at 230 °C and 5 kg | 25 | dg/min | ISO 1133 |
| at 230 °C and 2.16 kg | 5 | dg/min | ISO 1133 |
| Density ⁽¹⁾ | 960 | kg/m³ | ISO 1183 |
| Filler content | 10 | % | SABIC method |
| Mould shrinkage (2) | | | |
| 24 hours after injection moulding | 1.2 | % | SABIC method |
| MECHANICAL PROPERTIES (1) | | | |
| Tensile test | | | |
| Tensile modulus | 1300 | MPa | ISO 527/1A |
| stress at yield | 21 | MPa | ISO 527/1A |
| stress at break | 20 | MPa | ISO 527/1A |
| strain at break | 150 | % | ISO 527/1A |
| Flexural test | | | |
| Flexural modulus | 1400 | MPa | ISO 178/1A |
| Izod impact notched ⁽³⁾ | | | |
| at 23 °C | N.B. | kJ/m² | ISO 180/1A |
| at 0 °C | 10 | kJ/m² | ISO 180/1A |
| at -20 °C | 5.5 | kJ/m² | ISO 180/1A |
| THERMAL PROPERTIES (1) | | | |
| Heat deflection temperature | | | |
| at 0.45 MPa (HDT/B) | 90 | °C | ISO 75 |
| Coeff. of linear thermal expansion | | | |
| -30 °C to 100 °C | 100 | μm/mK | ISO 11359-2 |

- (1) Injection molded sample ISO527-1A
- (2) Injection molded plaque 65x65x3.2mm
- (3) N.B.: No Break



