

SABIC® PPCOMPOUND 1600

PP COMPOUND IMPACT MODIFIED

DESCRIPTION

SABIC®PPcompound 1600 is a medium flow, UV stabilized PP copolymer, developed for outdoor consumer injection molded applications. This material has been designed to combine a good performance profile with good processing.

SABIC® PPcompound 1600 is a designated injection molding grade for consumer applications.

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	3.7	dg/min	ISO 1133
Density ⁽¹⁾	907	kg/m ³	ISO 1183
Filler content	0	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	1.3	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile test			
Tensile modulus	1250	MPa	ISO 527/1A
stress at yield	23	MPa	ISO 527/1A
stress at break	17	MPa	ISO 527/1A
strain at break	157	%	ISO 527/1A
Flexural test			
Flexural modulus	1300	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	52	kJ/m ²	ISO 180/1A
at -20 °C	6.2	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	101	°C	ISO 75

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

