

SABIC® PPCOMPOUND 17T1022

PP COMPOUND MINERAL FILLED

DESCRIPTION

SABIC® PPcompound 17T1022 is a 22% talc filled grade which is high heat stabilized, developed for under the bonnet applications. This material has been designed to combine a good performance profile with good processing.

SABIC® PPcompound 17T1022 is a designated automotive grade.

IMDS ID: 202227823

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	15	dg/min	ISO 1133
Density ⁽¹⁾	1040	kg/m ³	ISO 1183
Filler content	20	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	1.2	%	SABIC method
MECHANICAL PROPERTIES ⁽¹⁾			
Tensile test			
Tensile modulus	2600	MPa	ISO 527/1A
stress at yield	31	MPa	ISO 527/1A
stress at break	25	MPa	ISO 527/1A
strain at break	13	%	ISO 527/1A
Flexural test			
Flexural modulus	2650	MPa	ISO 178/1A
Izod impact notched ⁽³⁾			
at 23 °C	2.1	kJ/m ²	ISO 180/1A
THERMAL PROPERTIES ⁽¹⁾			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	121	°C	ISO 75

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

(3) N.B.: No Break

