

SABIC® PPCOMPOUND 55T1030

PP COMPOUND MINERAL FILLED
REGION AMERICAS

DESCRIPTION

SABIC® PPcompound 55T1030 is a Polypropylene copolymer with 30% talcum. It is especially suited for applications that require an exceptional stiffness combined with a high impact resistance (even at low temperatures) like dashboard carriers and other dashboard components that are exposed to high temperatures.

SABIC® PPcompound 55T1030 is a designated automotive grade.

IMDS ID: 16160823

TYPICAL PROPERTY VALUES

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	21	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	16	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3.4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	45.6	%	ASTM D638
Tensile Modulus, 50 mm/min	2090	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	24	MPa	ISO 527
Tensile Stress, break, 50 mm/min, 1A	18	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.4	%	ISO 527
Tensile Strain, break, 50 mm/min	80	%	ISO 527
Tensile Modulus, 1 mm/min	2520	MPa	ISO 527
Flexural Modulus, 2 mm/min, 64mm span	2810	MPa	ISO 178
Hardness, Shore D	68	-	ISO 868
IMPACT			
Izod Impact, unnotched, 23°C, 63.5*12.7*3.2mm, Cut	1068	J/m	ASTM D4812
Izod Impact, notched, 23°C, 63.5*12.7*3.2mm, Cut	140	J/m	ASTM D256
Instrumented Impact Energy @ peak, 23°C @ 2.2 m/s	18	J	ASTM D3763
Izod Impact, notched, 23°C, 80*10*4mm, Cut	13	kJ/m²	ISO 180/1A
Izod Impact, notched, 0°C, 80*10*4mm, Cut	6	kJ/m²	ISO 180/1A
Izod Impact, notched, -30°C, 80*10*4mm, Cut	3	kJ/m²	ISO 180/1A
Charpy Impact, notched, 23°C, 80*10*4mm, Cut	13	kJ/m²	ISO 179/1eA
Charpy Impact, notched, -30°C, 80*10*4mm, Cut	1	kJ/m²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm	114	°C	ASTM D648
HDT, 1.82 MPa, 3.2 mm	60	°C	ASTM D648
CLTE, -30C to 100°C, flow	63	µm/mK	ISO 11359-2
CLTE, -30C to 100°C, xflow	94	µm/mK	ISO 11359-2
Vicat Softening 10N, 50°C/hr	150	°C	ISO 306
HDT 0.45 MPa, 80*10*4mm, Cut	120	°C	ISO 75-1&2
HDT 1.8 MPa, 80*10*4mm, Cut	64	°C	ISO 75-1&2



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Specific Gravity	1.14	-	ASTM D792
Density	1.13	g/cm ³	ISO 1183
Melt Flow Rate, 230°C/2.16 kg	4	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	210 – 270	°C	
Nozzle Temperature	210 – 270	°C	
Front - Zone 3 Temperature	210 – 270	°C	
Middle - Zone 2 Temperature	200 – 250	°C	
Rear - Zone 1 Temperature	190 – 230	°C	
Mold Temperature	15 – 60	°C	
Back Pressure	1 – 1.5	MPa	

