

Ultramid® 8202 HS

Polyamide 6

Product Description

Ultramid 8202 HS is a heat stabilized, low viscosity, general purpose PA6 injection molding. It possesses the combination of strength and toughness and has excellent chemical and abrasion resistance. The heat stabilizer system extends the retention of properties at the more elevated temperatures. Excellent in filling thin walls or areas.

Applications

Ultramid 8202 HS is generally recommended for drapery hardware, gears, fittings, furniture casters, bearings, handles, clips, fasteners and thin parts.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.13	
Mold Shrinkage (1/8" bar, in/in)		0.012	
Moisture, %	D-570		
(24 Hour)		1.6	
(50% RH)		2.7	
(Saturation)		9.5	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Yield, MPa (psi)	D-638		
-40C (-40F)		126 (18,300)	110 (16,000)
23C (73F)		79 (11,500)	36 (5,220)
80C (176F)		35 (5,070)	30 (4,350)
121C (250F)		25 (3,620)	20 (2,900)
Tensile Strength, Break, MPa (psi)	D-638		
23C (73F)		75 (10,900)	60 (8,700)
Elongation, Yield, %	D-638		
23C (73F)		4	16
80C (176F)		42	35
121C (250F)		36	40
Elongation, Break, %	D-638		
23C (73F)		55	>100
Flexural Modulus, MPa (psi)	D-790		
-40C (-40F)		3,010 (436,000)	3,660 (531,000)
23C (73F)		2,830 (410,000)	740 (107,000)
65C (149F)		500 (72,500)	-
90C (194F)		350 (50,700)	-
121C (250F)		305 (44,200)	-
Flexural Strength, MPa (psi)	D-790		
-40C (-40F)		170 (24,600)	154 (22,300)
23C (73F)		108 (15,700)	35 (5,070)
65C (149F)		30 (4,350)	-
90C (194F)		20 (2,900)	-
121C (250F)		17 (2,460)	-



Ultramid® 8202 HS



Rockwell Hardness, R Scale	D-785	119	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
-40C (-40F)		48 (0.9)	43 (0.8)
23C (73F)		58 (1.1)	NB
Drop Weight Impact, ft-lbs, 23C	BASF Drop Weight Impact Test	105	>200
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, C(F)	D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) C(F)	D-648	65 (149)	-
Heat Deflection @ 66 psi (.45 MPa) C(F)	D-648	178 (352)	-
Coef. of Linear Thermal Expansion, mm/mm C (in/in F)	E-831	0.83 X10-4	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 1.5mm	UL94	V-2	
Relative Temperature Index, 1.5mm	UL746B		
Mechanical w/o Impact, C		105	
Mechanical w/ Impact, C		105	
Electrical, C		130	
ELECTRICAL	ASTM Test Method	Dry	Conditioned
Volume Resistivity, 1.5 mm	D-257	>1E13	-
Dielectric Strength, Short Time, 1.5 mm	D-149	22	-

