

Ultramid® 8333G HI HS BK-106

Polyamide 6

Product Description

Ultramid 8333G HI HS BK-106 is a 33% glass reinforced, impact modified PA6 injection molding compound pigmented black developed for applications requiring improved dry as molded toughness in combination with a balance of strength, stiffness and excellent moldability/surface aesthetics.

Applications

Ultramid 8333G HI HS BK-106 is generally recommended for application such as front wheel chair wheels, bicycle wheels, power tool housings, chain saw housings, clips and fasteners, hose clamps and window hardware.

PHYSICAL	ASTM Test Method	Property Value	
Specific Gravity	D-792	1.36	
Mold Shrinkage (1/8" bar, in/in)		0.003	
Moisture, %	D-570		
(24 Hour)		0.9	
(50% RH)		1.5	
(Saturation)		5.5	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Break, MPa (psi)	D-638		
23C (73F)		145 (21,000)	-
Elongation, Break, %	D-638		
23C (73F)		2.5	-
Flexural Modulus, MPa (psi)	D-790		
23C (73F)		7,990 (1,160,000)	-
Flexural Strength, MPa (psi)	D-790		
23C (73F)		232 (33,600)	-
Rockwell Hardness, R Scale	D-785	121	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
23C (73F)		182 (3.4)	-
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, C(F)	D-3418	220 (428)	-
Heat Deflection @ 264 psi (1.8 MPa) C(F)	D-648	208 (406)	-

