

# Ultramid® HPN 9350 HS

## Polyamide 6

### Product Description

Ultramid HPN 9350 HS is a flexible, heat stabilized, impact modified PA6 extrusion grade resin. It possesses a balance of performance properties such as good flexibility, toughness and abrasion resistance. The addition of heat stabilizer system extends its retention of properties at elevated temperatures. Chemical resistance is excellent to greases, oils, and hydrocarbons.

### Applications

Ultramid HPN 9350 HS is generally recommended for applications such as automotive under hood tubing, windshield washer tubing, cable jacketing, and other tubing.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm	1183	1.06	
Moisture, %	62		
(50% RH)		1.9	
(Saturation)		6.8	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23C		1,700	-
Tensile stress at yield, MPa	527		
23C		45	-
Tensile strain at yield, %	527		
23C		4.5	-
Nominal strain at break, %	527		
23C		>50	-
Flexural Strength, MPa	178		
23C		50	-
Flexural Modulus, MPa	178		
23C		1,450	-
Ball Indentation, MPa	2039-1	70	-
IMPACT	ISO Test Method	Dry	Conditioned
Charpy Notched, kJ/m <sup>2</sup>	179		
23C		40	-
-30C		9	-
Charpy Unnotched, kJ/m <sup>2</sup>	179		
23C		N	-
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, C	3146	220	-
HDT A, C	75	50	-



Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.

## Typical Profile

Melt Temperature 240-250 degC (464-482 degF)

Typical Barrel Profile (degC):

Rear 245-260 degC (473-500 degF)  
Middle 240-255 degC (464-491 degF)  
Front 240-250 degC (464-482 degF)

Head 225-245 degC (437-473 degF)  
Flange 225-240 degC (437-464 degF)  
Die 225-240 degC (437-464 degF)

## Screw Parameters

Metering Section	40%
Transition Section	6 to 7 flights
Feed Section	balance of screw length
Compression Ratio	3.5:1 to 4.0:1
L/D Ratio	20:1 to 24:1

## Tooling & Sizing

Die to Finished Tube dia. 1.5-2.0:1

Selection of pin and die size will be dependent on the material viscosity. In general, the ratio of die size to finished tube diameter is about 1.5-2.0:1. The mandrel (pin) size is determined the same way in relation to the inner tube diameter.

Free (open tank) extrusion is recommended when producing tube diameters 1 cm and below. For larger diameters, a differential pressure vacuum tank is recommended.

Tooling draw ratio is generally higher with free extrusion versus sizing, but will depend on melt viscosity. The vacuum sizer entrance should be about 3-9% larger than the finished tube outer diameter. Selection will depend on melt viscosity and die swell of the extrudate.

## Quenching

For diameters less than or equal to 1 cm (.39") O.D., open tank quenching with normal tap water is suggested. Depending upon line speed, quenching distance can vary from 7.5 to 12 meters (24.6-39.4 feet). A short air gap (die to quench water) is recommended for both tubing and cable jacketing for best flexibility.

## Note



## Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

