Product Information

Ultramid[®] HPN 9350 HS Polyamide 6



Product Description

Ultramid HPN 9350 HS is a flexible, heat stabilized, impact modified PA6 extrusion grade resin. It possesses a balance of performance properties such as good flexibility, toughness and abrasion resistance. The addition of heat stabilizer system extends its retention of properties at elevated temperatures. Chemical resistance is excellent to greases, oils, and hydrocarbons.

Applications

Ultramid HPN 9350 HS is generally recommended for applications such as automotive under hood tubing, windshield washer tubing, cable jacketing, and other tubing.

PHYSICAL	ASTM Test Method	Property	y Value
Specific Gravity	D-792	1.0)6
Mold Shrinkage (1/8" bar, in/in)		0.0	13
Moisture, %	D-570		
(50% RH)		1.9	9
(Saturation)		6.8	
MECHANICAL	ASTM Test Method	Dry	Conditioned
Tensile Strength, Yield, MPa (psi)	D-638		
23C (73F)		50 (7,250)	-
Elongation, Yield, %	D-638		
23C (73F)		5	-
Elongation, Break, %	D-638		
23C (73F)		>100	-
Flexural Modulus, MPa (psi)	D-790		
-40C (-40F)		2,280 (331,000)	-
23C (73F)		1,730 (251,000)	520 (75,400)
65C (149F)		375 (54,400)	315 (45,700)
90C (194F)		220 (31,900)	240 (34,800)
121C (250F)		190 (27,600)	210 (30,400)
Flexural Strength, MPa (psi)	D-790		
-40C (-40F)		105 (15,200)	120 (17,400)
23C (73F)		69 (10,000)	25 (3,620)
65C (149F)		15 (2,170)	15 (2,170)
90C (194F)		10 (1,450)	10 (1,450)
121C (250F)		9.5 (1,380)	10 (1,450)
Rockwell Hardness, R Scale	D-785	80	-
IMPACT	ASTM Test Method	Dry	Conditioned
Notched Izod Impact, J/M (ft-lbs/in)	D-256		
23C (73F)		590 (11.0)	-
Drop Weight Impact, ft-lbs, 23C	BASF Drop Weight Impact Test	140	-
THERMAL	ASTM Test Method	Dry	Conditioned
Melting Point, C(F)	D-3418	220 (428)	-





Ultramid® HPN 9350 HS



Heat Deflection @ 264 psi ((1.8 MPa) C(F)	D-648	55 (131) -		
Processing Guidelines					
	Material Handling Max. Water content: 0.1% Product is supplied in sealed containers and drying prior to molding is not required. If drying becomes necessary, a dehumidifying or desiccant dryer operating at 80 degC (176 degF) is recommended. Drying time is dependent on moisture level, but 2-4 hours is generally sufficient. Further information concerning safe handling procedures can be obtained from the Material Safety Data Sheet. Alternatively, please contact your BASF representative.				
	Typical Profile Melt Temperature 240-250 degC (464-482 degF)				
	Typical Barrel Profile (degC):				
	Rear 245-260 degC (473-500 degF) Middle 240-255 degC (464-491 degF) Front 240-250 degC (464-482 degF)				
	Head 225-245 degC (437-473 degF) Flange 225-240 degC (437-464 degF) Die 225-240 degC (437-464 degF)				
Screw Parameters					
	Metering Section	40%			
	Transition Section	6 to 7 flights	;		
	Feed Section	balance of screw	ength		
	Compression Ratio	3.5:1 to 4.0:	L		
	L/D Ratio	20:1 to 24:1			
	Tooling & Sizing Die to Finished Tube dia. 1 Selection of pin and die siz	.5-2.0:1 e will be dependent on the	material viscosity. In general, the ratio of die		
	way in relation to the inner tube diameter.				

Tooling draw ratio is generally higher with free extrusion versus sizing, but will depend on melt viscosity. The vacuum sizer entrance should be about 3-9% larger than the finished tube outer diameter. Selection will depend on melt viscosity and die swell of the extrudate.

Quenching





larger diameters, a differential pressure vacuum tank is recommended.

Ultramid® HPN 9350 HS



For diameters less than or equal to 1 cm (.39") O.D., open tank quenching with normal tap water is suggested. Depending upon line speed, quenching distance can vary from 7.5 to 12 meters (24.6-39.4 feet). A short air gap (die to quench water) is recommended for both tubing and cable jacketing for best flexibility.

Note

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.



