

**Product description**

Ultramid® PSB 286 is an unreinforced polyamide PA6, with very good lubrication, standard for fast injection cycles, for injection moulding. This grade offers high fluidity and good mould release.

**Injection Notes**

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h.

**Injection Advice:**

- For unfilled polyamides, BASF SE recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

**Disclaimer**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

**Safety Information**

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

**Regulations Compliance**

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

**Customer Services**

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design



## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>General Properties</b>			
North America	-	-	<b>+</b>
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	<b>M</b>
Colour: black (bk), uncoloured (un), coloured (co), transparent (tr)	-	-	<b>bk,un</b>
<b>Physical</b>			
Water absorption, 24 h in water, 23 °C	ISO 62	%	<b>1.3</b>
Density	ISO 1183	kg/m <sup>3</sup>	<b>1140 / -</b>
<b>Mechanical properties</b>			
			<b>dry / cond.</b>
Tensile modulus	ISO 527-1/-2	MPa	<b>3000 / 1300</b>
Yield stress, 50 mm/min	ISO 527-1/-2	MPa	<b>85 / 45</b>
Stress at break	ISO 527-1/-2	MPa	<b>80 / 41</b>
Strain at break	ISO 527-1/-2	%	<b>65 / -</b>
Flexural modulus	ISO 178	MPa	<b>2800 / 1000</b>
Flexural strength	ISO 178	MPa	<b>115 / 40</b>
Charpy notched impact strength ISO 179/1eA (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	<b>5.5 / 81</b>
Charpy impact strength ISO 179-1eU (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	<b>N / -</b>
<b>Thermal properties</b>			
HDT B (0.45 MPa)	ISO 75-1/-2	°C	<b>80</b>
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	<b>222</b>
<b>Electrical properties</b>			
			<b>dry / cond.</b>
Surface resistivity	IEC 62631-3-2	Ohm	<b>1E14 / 1E12</b>
Volume resistivity	IEC 62631-3-1	Ohm*m	<b>1E13 / 1E11</b>
Electric strength (d = 2.0 mm)	IEC 60243-1	kV/mm	<b>- / 18</b>
Relative permittivity (100Hz)	IEC 62631-2-1	-	<b>3.2 / 3.9</b>
Dissipation factor (100 Hz)	IEC 62631-2-1	E-4	<b>0.023 / 0.1</b>
Comparative tracking index, CTI, test liquid A	IEC 60112	-	<b>600 / -</b>
<b>Flammability</b>			
Burning Behav. at 1.6 mm nom. thickn.	IEC 60695-11-10	class	<b>V-2</b>
Burning Behav. at thickness 0.8 mm	IEC 60695-11-10	class	<b>V-2</b>
Burning Behav. at thickness 3.2 mm	UL-94, IEC 60695	class	<b>V-2</b>
Glow Wire Flammability Index (0.8 mm)	IEC 60695-2-12	°C	<b>700</b>
Glow Wire Flammability Index (1.6 mm)	IEC 60695-2-12	°C	<b>700</b>
Glow Wire Flammability Index (3.2 mm)	IEC 60695-2-12	°C	<b>750</b>
<b>Injection</b>			
Pre/Post-processing, Pre-drying, Temperature	-	°C	<b>80</b>
Pre/Post-processing, max. allowed water content	-	%	<b>0.2</b>
Injection molding cylinder temperature 1 (feed zone)	-	°C	<b>230 - 235</b>
Injection molding cylinder temperature 2 (compression)	-	°C	<b>235 - 240</b>
Injection molding cylinder temperature 3 (metering-zone, head room of screw)	-	°C	<b>235 - 245</b>
injection molding, Mold temperature, range	ISO 294	°C	<b>60 - 80</b>

